



## Prodin Ferrite S.L.

Polígono Industrial "Molí dels Frares" Calle C/A - Nave 2  
08620 Sant Vicenç dels Horts - Barcelona - España  
T: +34 936 724 610  
info@prodinferrite.com - www.prodinferrite.com

RANGO DIAMETRO		MATERIAL GRADOS	
Diametro exterior	max. 600 mm	G.O.S.S. espesor	0.1
Diametro interior	min 10 mm	G.O.S.S. espesor	0.3
Ancho fleje	de 7 a 200 mm	HiB espesor	0.3

## ESPECIFICACIONES MAGNETICAS

Grado	Espec. No.	Espesor	Frecuencia	H eff	B min
G.O.S.S.	FS-0.3	0.3 mm	50 Hz	0,03 A/cm	0,0055 Tesla
				0,3 A/cm	1,4 Tesla
				10 A/cm	1,7 Tesla
G.O.S.S.	FS-06	0.3 mm	50 Hz	0,03 A/cm	0,085 Tesla
				0,3 A/cm	1,45 Tesla
HIB	FS-20	0.3 mm	50 Hz	0,03 A/cm	0,12 Tesla
				0,03 A/cm	1,6 Tesla
				1,0 A/cm	1,75 Tesla
G.O.S.S.	FS-40	0.1 mm	400 Hz	B	P max
				1.0 Tesla	8 W/kg