


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per Set)

- Effective Length (L_e): 57.9mm
- Effective Area (A_e): 108.7mm²
- Effective Area (A_{Min}): 107.4mm²
- Effective Volume (V_e): 6295mm³



Approximate weight (without Gap): 30.0 g/Set

“Clamp force for AL measurement is 20±10N, unless otherwise stated”

EE3011 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	μ_e approx.	P_V (W/set)	P_V (W/set)	P_V (W/set)	
CF295	3000 ±20%	5600 +30%/-20%	≈2400	≤0.69 (200mT, 25kHz, 100°C)	≤0.72 (100mT, 100kHz, 100°C)	≤3.78 (200mT, 100kHz, 100°C)	CF295 EE3011

