


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 65.5mm
- Effective Area (A_e): 104.6mm²
- Effective Area (A_{Min}): 103.8mm²
- Effective Volume (V_e): 6850mm³


Approximate weight (without Gap): 38.0g/Set



EE3012 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	
CF196	2000 \pm 20%	3300 +30%/-20%	\leq 0.87(200mT,16kHz,100°C)	
CF139	2100 \pm 20%	3450 +30%/-20%	\leq 0.62(100mT,100kHz,100°C)	
CF297	2300 \pm 20%	3600 +30%/-20%	\leq 0.56(100mT,100kHz,100°C)	



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value