



PRODUCT DATA APPROVAL

SHEET

Core- I10013A

Cosmo Ferrites Ltd.

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade**

Approximate weight (without Gap): 150g/Pc



I10013A (OL)


Material	Initial Permeability (μ_{iac})	AL Value (nH)	μ_e Approx.	P_v (W/set)
CF139	2100 \pm 20%	NA	NA	NA
CF297	2300 \pm 20%	NA	NA	NA
CF292	1800 \pm 20%	NA	NA	NA

Note : Only one face to be ground.

Dimensions

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	101.6	101.85	101.35
F	25.4	25.78	25.02
G	12.7	13.1	12.3

For Cosmo Ferrites Limited-INDIA
Checked
By:
A.K.



Prodin Ferrite S.L.

Calle A, 27, 08620 Sant Vicenç dels Horts, Barcelona (Spain)

Tel.: +34 93 672 46 10

info@prodinferrite.com

www.prodinferrite.com