

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, as per IEC standards.

Parameter	Value	Unit
Effective Length (L_e):	25.7	mm
Effective Area (A_e):	105	mm ²
Effective Area (A_{min}):	98	mm ²
Effective Volume (V_e):	2700	mm ³
Approximate weight(m):	16	g/set

Effective Parameters irrespective of material grade (per set)

“Clamping force for AL measurement is 50 ± 15 N, unless otherwise stated”



PQ2610 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL, N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	μ_e Approx./Set	P_v (W/set) 25kHz,200mT, 100°C	P_v (W/set) (100kHz,100mT, 100°C)	P_v (W/set) (100kHz,200mT, 100°C)
CF139	2100±20%	5900+30%/-20%	≈1150	≤ 0.30	≤0.27	≤ 1.49

