

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade (per piece)**

- Effective Length (L_e): 13.0 mm
- Effective Area (A_e): 3.4mm²
- Effective Area (A_{Min}): 3.4mm²
- Effective Volume (V_e): 44.0mm³



Approximate weight : 0.25g/pc

T0602 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 ±20%	650+30%/-20%
CF139	2100 ±20%	700+30%/-20%
CF130	3000 ±20%	1000+30%/-20%
CF195A	5000 ±20%	1600+30%/-20%
CF265	5000 ±20%	1600+30%/-20%
CF190	6000 ±20%	2000+30%/-20%
CF197	7000 ±20%	2300+30%/-20%
CF199	9000 ±20%	2900 ±30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	5.85	6.13	5.57
B	3.05	3.33	2.77
C	2.5	2.75	2.25

