

## PRODUCT SPECIFICATION DATA SHEET

**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade (per piece)**

Effective Length ( $L_e$ ): 15.5 mm

Effective Area ( $A_e$ ): 4.0mm<sup>2</sup>

Effective Area ( $A_{Min}$ ): 4.0mm<sup>2</sup>

Effective Volume ( $V_e$ ): 62.0mm<sup>3</sup>

**Approximate weight : 0.4g/pc**



T0702A OL (Un- Coated)

**Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C**

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	650+30%/-20%
CF139	2100 $\pm$ 20%	700+30%/-20%
CF130	3000 $\pm$ 20%	950+30%/-20%
CF195A	5000 $\pm$ 20%	1600+30%/-20%
CF265	5000 $\pm$ 20%	1600+30%/-20%
CF190	6000 $\pm$ 20%	1950+30%/-20%
CF197	7000 $\pm$ 20%	2300+30%/-20%
CF199	9000 $\pm$ 20%	2900 $\pm$ 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	7.2	7.4	7.0
B	3.3	3.5	3.1
C	2.3	2.5	2.1

