

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

Effective Length (L_e): 20.7 mm

Effective Area (A_e): 7.0mm²

Effective Area (A_{Min}): 7.0mm²

Effective Volume (V_e): 151mm³

Approximate weight : 0.8g/pc



T0903 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	850+30%/-20%
CF139	2100 \pm 20%	900+30%/-20%
CF130	3000 \pm 20%	1300+30%/-20%
CF195A	5000 \pm 20%	2100+30%/-20%
CF265	5000 \pm 20%	2100+30%/-20%
CF190	6000 \pm 20%	2500+30%/-20%
CF197	7000 \pm 20%	3000+30%/-20%
CF199	9000 \pm 20%	3800 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	9.53	9.83	9.23
B	4.75	4.95	4.55
C	3.18	3.38	2.98

