

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade (per piece)**

- Effective Length (L_e): 20.7 mm
- Effective Area (A_e): 8.75mm²
- Effective Area (A_{Min}): 8.75mm²
- Effective Volume (V_e): 181mm³

Approximate weight : 0.9g/pc



T0904 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	1050+30%/-20%
CF139	2100 \pm 20%	1100+30%/-20%
CF130	3000 \pm 20%	1600+30%/-20%
CF195A	5000 \pm 20%	2650+30%/-20%
CF265	5000 \pm 20%	2650+30%/-20%
CF190	6000 \pm 20%	3200+30%/-20%
CF197	7000 \pm 20%	3700+30%/-20%
CF199	9000 \pm 20%	4800 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	9.53	9.83	9.23
B	4.75	4.95	4.55
C	3.8	4.0	3.6



