

**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade (per piece)**

- Effective Length ( $L_e$ ): 25.1 mm
- Effective Area ( $A_e$ ): 8.0mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 8.0mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 200mm<sup>3</sup>

**Approximate weight : 1.1g/pc**



## T1004 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	800+30%/-20%
CF139	2100 $\pm$ 20%	850+30%/-20%
CF130	3000 $\pm$ 20%	1200+30%/-20%
CF195A	5000 $\pm$ 20%	1900+30%/-20%
CF265	5000 $\pm$ 20%	1900+30%/-20%
CF190	6000 $\pm$ 20%	2400+30%/-20%
CF197	7000 $\pm$ 20%	2800+30%/-20%
CF199	9000 $\pm$ 20%	3600 $\pm$ 30%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	10.0	10.3	9.7
B	6.0	6.2	5.8
C	4.0	4.3	3.7

