

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

Effective Length (L_e): 31.4 mm

Effective Area (A_e): 15.2mm²

Effective Area (A_{Min}): 15.2mm²

Effective Volume (V_e): 477mm³

Approximate weight : 2.45g/pc



T1306A OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 ±20%	1200+30%/-20%
CF139	2100 ±20%	1250+30%/-20%
CF130	3000 ±20%	1825+30%/-20%
CF195A	5000 ±20%	3050+30%/-20%
CF265	5000 ±20%	3050+30%/-20%
CF190	6000 ±20%	3650+30%/-20%
CF197	7000 ±20%	4250+30%/-20%
CF199	9000 ±20%	5500 ±30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	12.9	13.15	12.65
B	7.9	8.1	7.7
C	6.2	6.4	6.0

