

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade (per piece)**

- Effective Length (L_e): 35.0 mm
 - Effective Area (A_e): 12.1mm²
 - Effective Area (A_{Min}): 12.1mm²
 - Effective Volume (V_e): 422mm³
- Approximate weight : 2.1g/pc**



T1405 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	
CF196	2000 \pm 20%	880+30%/-20%	
CF139	2100 \pm 20%	900+30%/-20%	
CF130	3000 \pm 20%	1325+30%/-20%	
CF195A	5000 \pm 20%	2250+30%/-20%	
CF265	5000 \pm 20%	2250+30%/-20%	
CF190	6000 \pm 20%	2700+30%/-20%	
CF197	7000 \pm 20%	3100+30%/-20%	
CF199	9000 \pm 20%	4000 \pm 30%	

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	14.0	14.3	13.7
B	9.0	9.2	8.8
C	4.9	5.1	4.7

