

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 37.3 mm
- Effective Area (A_e): 78.1mm²
- Effective Area (A_{Min}): 78.1mm²
- Effective Volume (V_e): 2913mm³
Approximate weight : 14.0g/pc



T1528 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	5300+30%/-20%
CF139	2100 \pm 20%	5500+30%/-20%
CF130	3000 \pm 20%	7900+30%/-20%
CF195A	5000 \pm 20%	13100+30%/-20%
CF265	5000 \pm 20%	13100+30%/-20%
CF190	6000 \pm 20%	15800+30%/-20%
CF197	7000 \pm 20%	18400+30%/-20%
CF199	9000 \pm 20%	23700 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	15.15	15.65	14.65
B	9.5	9.9	9.1
C	28.15	28.55	27.75

