

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

Effective Length (L_e): 38.5 mm

Effective Area (A_e): 22.0mm²

Effective Area (A_{Min}): 22.0mm²

Effective Volume (V_e): 847mm³

Approximate weight : 4.5g/pc



T1607 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

| Material Grade | Initial Permeability (μ_{iac}) | AL Value (nH) |
|----------------|--------------------------------------|----------------|
| CF196 | 2000 \pm 20% | 1400+30%/-20% |
| CF139 | 2100 \pm 20% | 1500+30%/-20% |
| CF130 | 3000 \pm 20% | 2150+30%/-20% |
| CF195A | 5000 \pm 20% | 3600+30%/-20% |
| CF265 | 5000 \pm 20% | 3600+30%/-20% |
| CF190 | 6000 \pm 20% | 4300+30%/-20% |
| CF197 | 7000 \pm 20% | 5000+30%/-20% |
| CF199 | 9000 \pm 20% | 6450 \pm 30% |

Dimensions(Un-coated Core)

| Dimension | Nominal (in mm) | Maximum (in mm) | Minimum (in mm) |
|-----------|-----------------|-----------------|-----------------|
| A | 16.0 | 16.4 | 15.6 |
| B | 9.6 | 9.9 | 9.3 |
| C | 7.0 | 7.2 | 6.8 |

