

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 38.5 mm
- Effective Area ( $A_e$ ): 25.1mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 25.1mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 966mm<sup>3</sup>  
Approximate weight : 4.9g/pc



## T1608 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	1600+30%/-20%
CF139	2100 $\pm$ 20%	1700+30%/-20%
CF130	3000 $\pm$ 20%	2450+30%/-20%
CF195A	5000 $\pm$ 20%	4100+30%/-20%
CF265	5000 $\pm$ 20%	4100+30%/-20%
CF190	6000 $\pm$ 20%	4900+30%/-20%
CF197	7000 $\pm$ 20%	5700+30%/-20%
CF199	9000 $\pm$ 20%	7350 $\pm$ 30%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	16.0	16.5	15.5
B	9.6	10.0	9.2
C	8.0	8.3	7.7

