

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 34.8 mm
- Effective Area (A_e): 42.3mm²
- Effective Area (A_{Min}): 42.3mm²
- Effective Volume (V_e): 1472mm³
Approximate weight : 7.2g/pc



T1611 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3050+30%/-20%
CF139	2100 \pm 20%	3200+30%/-20%
CF130	3000 \pm 20%	4600+30%/-20%
CF195A	5000 \pm 20%	7600+30%/-20%
CF265	5000 \pm 20%	7600+30%/-20%
CF190	6000 \pm 20%	9100+30%/-20%
CF197	7000 \pm 20%	10700+30%/-20%
CF199	9000 \pm 20%	13700 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	16.0	16.5	15.5
B	8.0	8.4	7.6
C	11.0	11.4	10.6

