

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 44.4 mm
- Effective Area ( $A_e$ ): 39.9mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 39.9mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 1773mm<sup>3</sup>  
Approximate weight : 9.0g/pc



## T1910 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	2250+30%/-20%
CF139	2100 $\pm$ 20%	2350+30%/-20%
CF130	3000 $\pm$ 20%	3350+30%/-20%
CF195A	5000 $\pm$ 20%	5650+30%/-20%
CF265	5000 $\pm$ 20%	5650+30%/-20%
CF190	6000 $\pm$ 20%	6750+30%/-20%
CF197	7000 $\pm$ 20%	7900+30%/-20%
CF199	9000 $\pm$ 20%	10100 $\pm$ 30%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	19.0	19.4	18.6
B	10.8	11.1	10.5
C	10.0	10.3	9.7

