

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

Effective Length (L_e): 44.4 mm

Effective Area (A_e): 48.3mm²

Effective Area (A_{Min}): 48.3mm²

Effective Volume (V_e): 2145mm³

Approximate weight : 12.0g/pc



T1912 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 ±20%	2700+30%/-20%
CF139	2100 ±20%	2800+30%/-20%
CF130	3000 ±20%	4100+30%/-20%
CF195A	5000 ±20%	6800+30%/-20%
CF265	5000 ±20%	6800+30%/-20%
CF190	6000 ±20%	8200+30%/-20%
CF197	7000 ±20%	9500+30%/-20%
CF199	9000 ±20%	12500 ±30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	19.0	19.4	18.6
B	10.8	11.1	10.5
C	12.1	12.5	11.7

