

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

Effective Length (L_e): 43.6 mm

Effective Area (A_e): 33.6mm²

Effective Area (A_{Min}): 33.6mm²

Effective Volume (V_e): 1465mm³

Approximate weight : 7.9g/pc



T2007 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	1950+30%/-20%
CF139	2100 \pm 20%	2000+30%/-20%
CF130	3000 \pm 20%	2900+30%/-20%
CF195A	5000 \pm 20%	4850+30%/-20%
CF265	5000 \pm 20%	4850+30%/-20%
CF190	6000 \pm 20%	5800+30%/-20%
CF197	7000 \pm 20%	6800+30%/-20%
CF199	9000 \pm 20%	8700 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	20.0	20.4	19.6
B	10.0	10.25	9.75
C	7.0	7.3	6.7

