

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 43.6 mm
- Effective Area (A_e): 48.0mm²
- Effective Area (A_{Min}): 48.0mm²
- Effective Volume (V_e): 2092mm³
Approximate weight : 11.3g/pc



T2010 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

| Material Grade | Initial Permeability (μ_{iac}) | AL Value (nH) |
|----------------|--------------------------------------|-----------------|
| CF196 | 2000 \pm 20% | 2750+30%/-20% |
| CF139 | 2100 \pm 20% | 2900+30%/-20% |
| CF130 | 3000 \pm 20% | 4150+30%/-20% |
| CF195A | 5000 \pm 20% | 6900+30%/-20% |
| CF265 | 5000 \pm 20% | 6900+30%/-20% |
| CF190 | 6000 \pm 20% | 8300+30%/-20% |
| CF197 | 7000 \pm 20% | 9700+30%/-20% |
| CF199 | 9000 \pm 20% | 12400 \pm 30% |

Dimensions(Un-coated Core)

| Dimension | Nominal (in mm) | Maximum (in mm) | Minimum (in mm) |
|-----------|-----------------|-----------------|-----------------|
| A | 20.0 | 20.4 | 19.6 |
| B | 10.0 | 10.25 | 9.75 |
| C | 10.0 | 10.4 | 9.6 |

