

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 61.7 mm
- Effective Area (A_e): 30.8mm²
- Effective Area (A_{Min}): 30.8mm²
- Effective Volume (V_e): 1901mm³
Approximate weight : 9.2g/pc



T2506F OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	2050+30%/-20%
CF139	2100 \pm 20%	2100+30%/-20%
CF130	3000 \pm 20%	3000+30%/-20%
CF195A	5000 \pm 20%	5100+30%/-20%
CF265	5000 \pm 20%	5100+30%/-20%
CF190	6000 \pm 20%	6100+30%/-20%
CF197	7000 \pm 20%	7100+30%/-20%
CF199	9000 \pm 20%	9100 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	25.4	26.0	24.8
B	15.5	16.0	15.0
C	6.35	6.6	6.1

