

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 62.3 mm
- Effective Area ( $A_e$ ): 65.4mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 65.4mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 4074mm<sup>3</sup>  
Approximate weight : 19.0g/pc



## T2513 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	2600+30%/-20%
CF139	2100 $\pm$ 20%	2750+30%/-20%
CF130	3000 $\pm$ 20%	3950+30%/-20%
CF195A	5000 $\pm$ 20%	6600+30%/-20%
CF265	5000 $\pm$ 20%	6600+30%/-20%
CF190	6000 $\pm$ 20%	7900+30%/-20%
CF197	7000 $\pm$ 20%	9200+30%/-20%
CF199	9000 $\pm$ 20%	11900 $\pm$ 30%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	25.0	25.5	24.5
B	15.05	15.55	14.55
C	13.0	13.5	12.5

