

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 62.6 mm
- Effective Area (A_e): 79.4mm²
- Effective Area (A_{Min}): 79.4mm²
- Effective Volume (V_e): 4970mm³
Approximate weight : 26.19g/pc



T2813A OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3200+30%/-20%
CF139	2100 \pm 20%	3350+30%/-20%
CF130	3000 \pm 20%	4800+30%/-20%
CF195A	5000 \pm 20%	8000+30%/-20%
CF265	5000 \pm 20%	8000+30%/-20%
CF190	6000 \pm 20%	9500+30%/-20%
CF197	7000 \pm 20%	11100+30%/-20%
CF199	9000 \pm 20%	14300 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	27.5	28.1	26.9
B	14.9	15.3	14.5
C	13.0	13.4	12.6

