

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 61.0 mm
- Effective Area ( $A_e$ ): 100.2mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 100.2mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 6110mm<sup>3</sup>  
Approximate weight : 29.5g/pc



## T2815 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	4100+30%/-20%
CF139	2100 $\pm$ 20%	4300+30%/-20%
CF130	3000 $\pm$ 20%	6200+30%/-20%
CF195A	5000 $\pm$ 20%	10300+30%/-20%
CF265	5000 $\pm$ 20%	10300+30%/-20%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	28.0	28.7	27.3
B	14.0	14.5	13.5
C	14.9	15.3	14.5

