

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 72.5 mm
- Effective Area (A_e): 54.5mm²
- Effective Area (A_{Min}): 54.5mm²
- Effective Volume (V_e): 3951mm³
Approximate weight : 20.0g/pc



T2910 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	1900+30%/-20%
CF139	2100 \pm 20%	2000+30%/-20%
CF130	3000 \pm 20%	2800+30%/-20%
CF195A	5000 \pm 20%	4700+30%/-20%
CF265	5000 \pm 20%	4700+30%/-20%
CF190	6000 \pm 20%	5650+30%/-20%
CF197	7000 \pm 20%	6600+30%/-20%
CF199	9000 \pm 20%	8500 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	29.5	30.2	28.8
B	18.4	19.0	17.8
C	10.0	10.4	9.6

