

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 76.0 mm
- Effective Area (A_e): 58.1mm²
- Effective Area (A_{Min}): 58.1mm²
- Effective Volume (V_e): 4420mm³
Approximate weight : 29.0g/pc



T3109 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	1900+30%/-20%
CF139	2100 \pm 20%	2000+30%/-20%
CF130	3000 \pm 20%	2850+30%/-20%
CF195A	5000 \pm 20%	4800+30%/-20%
CF265	5000 \pm 20%	4800+30%/-20%
CF190	6000 \pm 20%	5800+30%/-20%
CF197	7000 \pm 20%	6700+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	31.5	32.5	30.5
B	19.0	19.6	18.4
C	9.5	9.9	9.1

