

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 76.0 mm
- Effective Area (A_e): 93.8mm²
- Effective Area (A_{Min}): 93.8mm²
- Effective Volume (V_e): 7129mm³
Approximate weight : 34.5g/pc



T3115 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

| Material Grade | Initial Permeability (μ_{iac}) | AL Value (nH) |
|----------------|--------------------------------------|-----------------|
| CF196 | 2000 \pm 20% | 3100+30%/-20% |
| CF139 | 2100 \pm 20% | 3250+30%/-20% |
| CF130 | 3000 \pm 20% | 4650+30%/-20% |
| CF195A | 5000 \pm 20% | 7700+30%/-20% |
| CF265 | 5000 \pm 20% | 7700+30%/-20% |
| CF190 | 6000 \pm 20% | 9300+30%/-20% |
| CF197 | 7000 \pm 20% | 10800+30%/-20% |
| CF199 | 9000 \pm 20% | 14000 \pm 30% |

Dimensions(Un-coated Core)

| Dimension | Nominal (in mm) | Maximum (in mm) | Minimum (in mm) |
|-----------|-----------------|-----------------|-----------------|
| A | 31.5 | 32.5 | 30.5 |
| B | 19.0 | 19.6 | 18.4 |
| C | 15.0 | 15.4 | 14.6 |

