

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 89.6 mm
- Effective Area (A_e): 108.7mm²
- Effective Area (A_{Min}): 108.7mm²
- Effective Volume (V_e): 9742mm³
Approximate weight : 47.5g/pc



T3617 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3050+30%/-20%
CF139	2100 \pm 20%	3200+30%/-20%
CF130	3000 \pm 20%	4550+30%/-20%
CF195A	5000 \pm 20%	7600+30%/-20%
CF265	5000 \pm 20%	7600+30%/-20%
CF190	6000 \pm 20%	9100+30%/-20%
CF197	7000 \pm 20%	10600+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	36.0	36.7	35.3
B	23.0	23.5	22.5
C	17.0	17.4	16.6

