

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 89.6 mm
- Effective Area ( $A_e$ ): 95.9mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 95.9mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 8593mm<sup>3</sup>  
Approximate weight : 40g/pc



## T3618 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	2700+30%/-20%
CF139	2100 $\pm$ 20%	2800+30%/-20%
CF130	3000 $\pm$ 20%	4000+30%/-20%
CF195A	5000 $\pm$ 20%	6700+30%/-20%
CF265	5000 $\pm$ 20%	6700+30%/-20%
CF190	6000 $\pm$ 20%	8000+30%/-20%
CF197	7000 $\pm$ 20%	9400+30%/-20%
CF199	9000 $\pm$ 20%	12100 $\pm$ 30%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	36.0	36.7	35.3
B	23.0	23.5	22.5
C	18.0	18.4	17.6

