

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 97.1 mm
- Effective Area (A_e): 77.5mm²
- Effective Area (A_{Min}): 77.5mm²
- Effective Volume (V_e): 7525mm³
Approximate weight : 38.9g/pc



T3813 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	2000+30%/-20%
CF139	2100 \pm 20%	2100+30%/-20%
CF130	3000 \pm 20%	3000+30%/-20%
CF195A	5000 \pm 20%	5000+30%/-20%
CF265	5000 \pm 20%	5000+30%/-20%
CF190	6000 \pm 20%	6000+30%/-20%
CF197	7000 \pm 20%	7000+30%/-20%
CF199	9000 \pm 20%	8500 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	38.1	38.6	37.6
B	25.4	25.9	24.9
C	12.7	12.9	12.5

