

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 89.7 mm
- Effective Area (A_e): 144.4mm²
- Effective Area (A_{Min}): 144.4mm²
- Effective Volume (V_e): 12953mm³
Approximate weight : 66.5g/pc



T3819A OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	4000+30%/-20%
CF139	2100 \pm 20%	4200+30%/-20%
CF130	3000 \pm 20%	6000+30%/-20%
CF195A	5000 \pm 20%	10100+30%/-20%
CF265	5000 \pm 20%	10100+30%/-20%
CF190	6000 \pm 20%	12100+30%/-20%
CF197	7000 \pm 20%	14100+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	38.0	38.6	37.4
B	22.0	22.45	21.55
C	18.5	18.85	18.15

