

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 82.8 mm
- Effective Area (A_e): 192.7mm²
- Effective Area (A_{Min}): 192.7mm²
- Effective Volume (V_e): 15956mm³
Approximate weight : 85g/pc



T3821 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	5850+30%/-20%
CF139	2100 \pm 20%	6100+30%/-20%
CF130	3000 \pm 20%	8700+30%/-20%
CF195A	5000 \pm 20%	14600+30%/-20%
CF265	5000 \pm 20%	14600+30%/-20%
CF190	6000 \pm 20%	16000+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	38.1	38.8	37.4
B	19.0	19.5	18.5
C	21.0	21.5	20.5

