

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 89.7 mm
- Effective Area (A_e): 226.3mm²
- Effective Area (A_{Min}): 226.3mm²
- Effective Volume (V_e): 20303mm³
Approximate weight : 100g/pc



T3829 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	6300+30%/-20%
CF139	2100 \pm 20%	6600+30%/-20%
CF130	3000 \pm 20%	9500+30%/-20%
CF195A	5000 \pm 20%	15800+30%/-20%
CF265	5000 \pm 20%	15800+30%/-20%
CF190	6000 \pm 20%	17400+30%/-20%
CF197	7000 \pm 20%	20600+30%/-20%
CF199	9000 \pm 20%	25000 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	38.0	38.6	37.4
B	22.0	22.45	21.55
C	29.0	29.5	28.5

