

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 96.4 mm
- Effective Area (A_e): 123.8mm²
- Effective Area (A_{Min}): 123.8mm²
- Effective Volume (V_e): 11934mm³
Approximate weight : 58.7g/pc



T4016 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3200+30%/-20%
CF139	2100 \pm 20%	3400+30%/-20%
CF130	3000 \pm 20%	4800+30%/-20%
CF195A	5000 \pm 20%	8000+30%/-20%
CF265	5000 \pm 20%	8000+30%/-20%
CF190	6000 \pm 20%	9700+30%/-20%
CF197	7000 \pm 20%	11300+30%/-20%
CF199	9000 \pm 20%	13700 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	39.9	40.5	39.3
B	24.1	24.6	23.6
C	16.0	16.3	15.7

