

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 103.0 mm
- Effective Area (A_e): 95.7mm²
- Effective Area (A_{Min}): 95.7mm²
- Effective Volume (V_e): 9857mm³
Approximate weight : 47.5g/pc



T4212 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	2300+30%/-20%
CF139	2100 \pm 20%	2450+30%/-20%
CF130	3000 \pm 20%	3500+30%/-20%
CF195A	5000 \pm 20%	5800+30%/-20%
CF265	5000 \pm 20%	5800+30%/-20%
CF190	6000 \pm 20%	7000+30%/-20%
CF197	7000 \pm 20%	8200+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	41.8	42.8	40.8
B	26.2	26.8	25.6
C	12.5	12.8	12.2

