

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 91.5 mm
- Effective Area ( $A_e$ ): 186.7mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 186.7mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 17083mm<sup>3</sup>  
Approximate weight : 90g/pc



## T4218 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	5100+30%/-20%
CF139	2100 $\pm$ 20%	5400+30%/-20%
CF130	3000 $\pm$ 20%	7700+30%/-20%
CF195A	5000 $\pm$ 20%	12800+30%/-20%
CF265	5000 $\pm$ 20%	12800+30%/-20%
CF190	6000 $\pm$ 20%	15300+30%/-20%
CF197	7000 $\pm$ 20%	17900+30%/-20%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	42.0	42.6	41.4
B	21.0	21.5	20.5
C	18.5	18.9	18.4

