

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 103.0 mm
- Effective Area (A_e): 137.9mm²
- Effective Area (A_{Min}): 137.9mm²
- Effective Volume (V_e): 14204mm³
Approximate weight : 79g/pc



T4218A OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3400+30%/-20%
CF139	2100 \pm 20%	3500+30%/-20%
CF130	3000 \pm 20%	5000+30%/-20%
CF195A	5000 \pm 20%	8400+30%/-20%
CF265	5000 \pm 20%	8400+30%/-20%
CF190	6000 \pm 20%	10100+30%/-20%
CF197	7000 \pm 20%	11700+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	41.8	42.8	40.8
B	26.2	26.8	25.6
C	18.0	18.5	17.5

