

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 128.7 mm
- Effective Area (A_e): 197.5mm²
- Effective Area (A_{Min}): 197.5mm²
- Effective Volume (V_e): 25430mm³
Approximate weight : 120g/pc



T5025 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3850+30%/-20%
CF139	2100 \pm 20%	4050+30%/-20%
CF130	3000 \pm 20%	5800+30%/-20%
CF195A	5000 \pm 20%	9600+30%/-20%
CF265	5000 \pm 20%	9600+30%/-20%
CF190	6000 \pm 20%	11500+30%/-20%
CF197	7000 \pm 20%	13500+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	50.0	51.0	49.0
B	34.0	34.8	33.2
C	25.0	25.5	24.5

