

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 128.7 mm
- Effective Area (A_e): 237.0mm²
- Effective Area (A_{Min}): 237.0mm²
- Effective Volume (V_e): 30516mm³
Approximate weight : 155g/pc



T5030 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	4600+30%/-20%
CF139	2100 \pm 20%	4850+30%/-20%
CF130	3000 \pm 20%	6950+30%/-20%
CF195A	5000 \pm 20%	11500+30%/-20%
CF265	5000 \pm 20%	11500+30%/-20%
CF190	6000 \pm 20%	13800+30%/-20%
CF197	7000 \pm 20%	16200+30%/-20%
CF199	9000 \pm 20%	18500 \pm 30%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	50.0	51.0	49.0
B	34.0	34.8	33.2
C	30.0	30.6	29.4

