

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 131.3 mm
- Effective Area (A_e): 210.5mm²
- Effective Area (A_{Min}): 210.5mm²
- Effective Volume (V_e): 27625mm³
Approximate weight : 135g/pc



T5618OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	4000+30%/-20%
CF139	2100 \pm 20%	4200+30%/-20%
CF130	3000 \pm 20%	6000+30%/-20%
CF195A	5000 \pm 20%	10000+30%/-20%
CF265	5000 \pm 20%	10000+30%/-20%
CF190	6000 \pm 20%	12000+30%/-20%
CF197	7000 \pm 20%	14100+30%/-20%

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	56.0	57.2	54.8
B	32.0	32.65	31.35
C	18.0	18.5	17.5

