

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 130.7 mm
- Effective Area ( $A_e$ ): 288.3mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 288.3mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 37681mm<sup>3</sup>  
Approximate weight : 200g/pc



## T6020OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	5500+30%/-20%
CF139	2100 $\pm$ 20%	5800+30%/-20%
CF130	3000 $\pm$ 20%	8300+30%/-20%
CF195A	5000 $\pm$ 20%	13800+30%/-20%
CF265	5000 $\pm$ 20%	13800+30%/-20%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	60.0	61.0	59.0
B	30.0	30.8	29.2
C	20.0	20.5	19.5

