

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 165.4mm
- Effective Area (A_e): 213.6mm²
- Effective Area (A_{Min}): 213.6mm²
- Effective Volume (V_e): 35328mm³
Approximate weight : 184.6g/pc



T7313 OL (Un-Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)
CF196	2000 \pm 20%	3250 +30%/-20%
CF139	2100 \pm 20%	3400 +30%/-20%
CF130	3000 \pm 20%	4800 +30%/-20%
CF195A	5000 \pm 20%	8100 +30%/-20%
CF265	5000 \pm 20%	8100 +30%/-20%
CF190	6000 \pm 20%	9700 +30%/-20%
CF197	7000 \pm 20%	11400 +30%/-20%
CF199	9000 \pm 20%	13000 \pm 30%

Dimensions :(Un-coated Cores)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	73.7	75.2	72.2
B	38.9	39.7	38.1
C	12.7	13.0	12.4

