

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 269.8mm
- Effective Area (A_e): 400.0mm²
- Effective Area (A_{Min}): 397.9mm²
- Effective Volume (V_e): 10792mm³

Approximate weight (without Gap): 571gm/Set



UU7020 Un-gapped (OL)

Test Conditions: 1 KHz/1mT/N=100/25°C

| Material | Initial Permeability (μ_{iac}) | AL Value (nH) | μ_e Approx. | P_v (W/set) |
|----------|--------------------------------------|----------------|--------------------|----------------------------|
| CF196 | 2000 \pm 20% | 3450 +30%/-20% | 1900 | <14.9(200mT,16kHz, 100°C) |
| CF139 | 2100 \pm 20% | 3600 +30%/-20% | 1950 | <10.8(100mT,100kHz, 100°C) |
| CF297 | 2300 \pm 20% | 3800 +30%/-20% | 2100 | <9.7(100mT,100kHz, 100°C) |

| Dimension | Nominal (in mm) | Maximum (in mm) | Minimum (in mm) |
|-----------|--------------------|--------------------|--------------------|
| A | 68.4 | 70.0 | 66.8 |
| B | 28.4 | 29.0 | 27.8 |
| C | 57.5 | 58.0 | 57.0 |
| D | 37.5 | 38.0 | 37.0 |
| E | 20.0 | 20.5 | 19.5 |

Dimensions :

