

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, as per IEC standards. Effective Parameters irrespective of material grade (per set)

Parameter	Value	Unit
Effective Length (L_e):	258.8	mm
Effective Area (A_e):	400	mm ²
Effective Area (A_{min}):	397.9	mm ²
Effective Volume (V_e):	103520	mm ³
Approximate weight(m):	529	g/set



UU8020 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL, N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	μ_e Approx. / Set	P_v (W/set) (25kHz,200mT, 100°C)	P_v (W/set) (100kHz,100mT, 100°C)
CF139	2100±20%	3900 +30%/-20%	≈2010	≤ 16.05	≤15.01
CF297	2300±20%	4200 +30%/-20%	≈2140	≤ 14.5	≤12.94

