


SPECIFICATION FOR APPROVAL

1. Material

Production:	Iron Powder Cores
P/N:	T250-52
A_L :	$242(\text{nH}/\text{N}^2) \pm 10\%$
Material:	-52
Coating Color:	Green/Blue
Coating material:	epoxy
Coating Breakdown Voltage:	800Vrms.0.5mA2sec




2. Physical Characteristics

After Coating			ℓ_e (cm)	A_e (cm ²)	V (cm ³)	W (cm ²)	Weight	Box Quantity (Pieces)
OD mm	ID mm	Ht mm						
63.50 ± 0.75	31.80 ± 0.75	25.40 ± 0.75	15.000	3.840	57.400	7.938	412.48g	56


3. Electrical Parameters(Typical) Temperature(25°C ± 2°C)

Test Item	Test Condition	Value(Typical)
Inductance	ϕ 0.29mm/10Ts, 10kHz/1V, $I_{DC}=0A$	24.20 μ H ± 10%
DC-Bias	ϕ 0.5mm/85Ts, 10kHz/1V, L(7.0A)/L(0A) × 100%($H_{DC}=50Oe$)	53%(Min.)
Core Loss	100kHz/140Gs	67mW/cm ³ (Max.)
Q	ϕ 0.29mm/10Ts, 200kHz/1V, $I_{DC}=0A$	16(Min.)
Remarks		

DC-Bias Curves(Typical)



Core Loss Curves(Typical)



Prodin Ferrite S.L.

Calle A, 27, 08620 Sant Vicenç dels Horts, Barcelona (Spain)

Tel.: +34 93 672 46 10

info@prodinferrite.com www.prodinferrite.com