


**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

**Effective Parameters irrespective of material grade (per set)**

- Effective Length ( $L_e$ ): 285.4mm
- Effective Area ( $A_e$ ): 792.7mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 757.9mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 226230mm<sup>3</sup>

**Approximate Weight: 1100g/Set**



## EE12820 Un-gapped (OL)

**Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C**

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)/Set	Ordering code
CF295	3000 $\pm$ 20%	7400 +30%/-20%	CF295 EE12820

## Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	130.0	133.0	127.0
B	-	-	89.0
C	63.0	64.0	62.0
D	43.0	43.5	42.5
E	40.0	41.0	39.0
F	20.0	21.0	19.0

