


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 29.6mm
 - Effective Area (A_e): 13.0mm²
 - Effective Area (A_{Min}): 12.4mm²
 - Effective Volume (V_e): 385mm³
- Approximate Weight (without Gap): 1.8g/Set**



EE1304 Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_V (W/set)	Ordering code
CF295	3000 ± 20%	950 +30%/-20%	≤0.045 (100mT,100KHz, 100°C)	CF295 EE1304

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	12.65	13.1	12.2
B	9.2	9.5	8.9
C	6.5	6.5	6.3
D	4.5	4.8	4.5
E	3.7	3.7	3.4
F	3.7	3.7	3.4

