


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 37.6mm
 - Effective Area (A_e): 20.1mm²
 - Effective Area (A_{Min}): 19.4mm²
 - Effective Volume (V_e): 756mm³
- Approximate Weight (without Gap): 3.6g/Set**



EE1605 Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF295	3000 \pm 20%	1300 +30%/-20%	\leq 0.09 (100mT,100kHz, 100°C)	CF295 EE1605

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	16.0	16.7	15.5
B	11.4	11.9	11.4
C	8.2	8.2	7.9
D	5.9	6.1	5.7
E	4.7	4.7	4.4
F	4.7	4.7	4.3

