

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 38mm
- Effective Area (A_e): 25mm²
- Effective Area (A_{Min}): 24.5mm²
- Effective Volume (V_e): 950mm³

Approximate weight (without Gap): 4.8g/Set

“Clamping force for AL measurement is 20±10N, Unless otherwise stated”



EE1905 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iAC})	AL Value (nH)	μ_e approx.	P_V (W/set)	P_V (W/set)	Ordering code
CF295	3000 ±20%	1500 +30%/-20%	≈1850	≤0.012(100mT,100kHz, 100°C)	≤0.57(200mT,100kHz, 100°C)	CF295 EE1905 OL

