


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 39.6mm
 - Effective Area (A_e): 22.5mm²
 - Effective Area (A_{Min}): 21.8mm²
 - Effective Volume (V_e): 891mm³
- Approximate Weight (without Gap): 4.8g/Set**



EE1905A Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	P_v (W/set)	Ordering code
CF295	3000 \pm 20%	1400 +30%/-20%	<0.10 (100mT,100kHz,100°C)	CF295 EE1905A

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	19.0	19.4	18.6
B	14.3	14.6	14.0
C	8.0	8.13	7.87
D	-	-	5.7
E	4.8	5.0	4.6
F	4.8	5.0	4.6

